

CL 20ES Stainless steel

Stainless steel (powder), chemical composition according to 1.4404, X 2 CrNiMo 17 13 2, 316L

CL 20ES is an austenitic stainless steel for the production of functional parts or components for pre-production moulds.

26

Fe

55,847

CHEMICAL COMPOSITION

Component	Indicative value (%)
Fe	Balance
Cr	16,5 - 18,5
Ni	10,0 - 13,0
Mo	2,0 - 2,5
Mn	0 - 2,0
Si	0 - 1,0
P	0 - 0,045
C	0 - 0,030
S	0 - 0,030

